

Electronic Raman scattering on under-doped $Hg - 1223$ high- T_c superconductors: investigations on the symmetry of the order parameter

A. Sacuto, J. Cayssol, D. Colson[†] and P. Monod

Laboratoire de Physique de la Matière Condensée, Ecole Normale Supérieure, 24 rue Lhomond, 75231 Paris cedex 05 France.

[†]*Physique de l'Etat Condensée, DRECAM/SPEC, CEA Saclay, 91191, Gif sur Yvette, France.*

(Received February 1, 2008)

Abstract

In order to obtain high quality, reliable electronic Raman spectra of a high- T_c superconductor compound, comparable with existing model, we have studied strongly under-doped $HgBa_2Ca_2Cu_3O_{8+\delta}$. This choice was made such as to i) minimize oxygen disorder in the Hg -plane generated by oxygen doping ii) avoid the need of phonon background subtraction from the raw data iii) eliminate traces of parasitic phases identified and monitored on the crystal surface. Under these experimental conditions we are able to present the pure electronic Raman response function in the B_{2g} , B_{1g} , $A_{1g} + B_{2g}$ and $A_{1g} + B_{1g}$ channels. The B_{2g} spectrum exhibits a linear frequency dependence (exponent $n = 1.12 \pm 0.03$) at low energy whereas the B_{1g} one shows a cubic-like dependence ($n = 3.02 \pm 0.1$). The B_{2g} and B_{1g} spectra display two well defined maxima at $5.6 k_B T_c$ and $9 k_B T_c$ respectively. In mixed A_{1g} channels an intense electronic peak centered around $6.4 k_B T_c$ is observed. The low energy parts of the spectra (below 350 cm^{-1}) correspond to the electronic response expected for a pure $d_{x^2-y^2}$ gap symmetry (and can be fitted up to the gap energy for the B_{1g} channel). However, in the upper parts (above 350 cm^{-1}), the relative position of the B_{1g} and B_{2g} peaks needs expanding the B_{2g} Raman vertex to second order Fermi surface harmonics to fit the data with the $d_{x^2-y^2}$ model. The sharper and more intense A_{1g} peak appears to challenge the Coulomb screening efficiency present for this channel. As compared to previous data on more optimally doped, less stoichiometric $Hg - 1223$ compounds, this work reconciles the electronic Raman spectra of under-doped $Hg - 1223$ crystals with the $d_{x^2-y^2}$ model, provided that the oxygen doping is not too strong. This apparent extreme sensitivity of the electronic Raman spectra to the low lying excitations induced by oxygen doping in the superconducting state is emphasized here and remains an open question.

Typeset using REVTeX

I. INTRODUCTION

Most of the recent investigations of inelastic light scattering by free carriers (electronic Raman scattering) on high- T_c superconductors are focused on the low energy electronic spectra (up to the gap energy) obtained for different polarizations of the incident and scattered light. These experiments are carried out in order to study the angular dependence of the superconducting order parameter. Indeed, theoretical calculations initiated by Devereaux et al. [1] predicted specific power laws of the electronic Raman intensity at low energy depending on the superconducting gap symmetry and the light polarization. More precisely, for a $d_{x^2-y^2}$ gap (or a $|d_{x^2-y^2}|$ gap since Raman scattering is not phase sensitive), the A_{1g} and B_{2g} symmetries involved (deduced respectively from parallel and crossed polarizations along Cu-O direction) should display a linear frequency dependence whereas the B_{1g} symmetry (obtained from crossed polarisations at 45 degrees from the Cu-O direction) should exhibit a cubic frequency dependence below the gap energy.

In order to carry out with reasonable confidence such an investigation a number of experimental difficulties must be overcome. The main reason for the occurrence of these difficulties stems out of the intrinsic weakness of the electronic Raman intensity which tends to be easily hindered by other contributions to the spectra. These originate from i) phonons scattering, ii) parasitic phases (luminescence or Raman) and iii) the effect of disorder.

The aim of this paper is to present clean and reliable electronic Raman measurements on high- T_c superconductors. This implies to find the appropriate high- T_c superconductor which allow us to eliminate the extra scattering contribution mentioned just above. We briefly discuss below each of these various contributions together with their possible cure.

The first major experimental difficulty is that in most compounds e.g. $La_{2-x}Sr_xCuO_4$, $YBa_2Cu_3O_{7-\delta}$ ($Y-123$), $Bi_2Sr_2CaCu_2O_{8+\delta}$ ($Bi-2212$) and $Tl_2Ba_2CuO_{6+\delta}$ ($Tl-2201$), an intense phonon structure is observed together with the weaker continuum of the electronic excitations. [2–5] In order to study the pure electronic Raman response function the phonon peaks have to be subtracted from the spectra. Vibrational structures are experimentally defined from the N state spectra and removed from the S state one. Without considering other contribution, this procedure cannot take into account the phonon temperature dependence (changes on the lineshape and intensity). The intrinsic weakness of the electronic Raman scattering, resulting in a moderate signal to noise ratio, makes this procedure awkward. Despite these difficulties, qualitative agreement has been found with the $d_{x^2-y^2}$ model [2–5] although the exponent for the power law of the B_{1g} channel is often exceedingly dependent on the phonon subtraction protocol. Raw data (before subtraction of phonons) frequently exhibit an ambiguous exponent of the power law of the B_{1g} channel. An attempt to avoid this problem [6] consisted to work on $Tl-2201$ superconductor, staying out of resonance of the phononic scattering by the use of the red excitation line. Qualitative agreement with the $d_{x^2-y^2}$ model for the stoichiometric compound was obtained from raw data (without subtraction of phonon) in B_{1g} channel.

In our previous work, in contrast with the above mentioned compounds, we observed that the $HgBa_2Ca_2Cu_3O_{8+\delta}$ compounds exhibit much lower intensity phonon lines (about one order of magnitude) for polarization lying into the CuO_2 planes. [7,8]. The decrease of the Raman activity of the B_{1g} phonon can be understood by symmetry considerations with respect to the CuO_2 layer. Indeed it has been shown [9] that the B_{1g} Raman phonon activity

increases with the crystal electric field induced by the cationic planes above and below the CuO_2 plane. In the $Hg - 1223$ mercurate the charge equivalence of the two cations (Ba^{2+} and Ca^{2+}) minimizes the local electric field and thus reduces the Raman phonon activity. Conversely in the $Y - 123$ compound where two differently charged cations (Y^{3+} , Ba^{2+}) are present above and below the CuO_2 plane, the Raman phonon activity is enhanced.

This favourable situation allowed us to carry out analysis of the Raman electronic spectra in the normal and superconducting states without dealing with the delicate handling of "phonon subtraction". Another advantage to work with mercurates is that these compounds belong to the highest T_c cuprate family which provides a larger spectral range below the superconducting gap frequency where the low-energy electronic spectrum can be analyzed.

The second major difficulty is due to the presence of parasitic phases on the surface of crystal mercurates. We have measured several $Hg - 1223$ single crystals from various batches corresponding to different oxygen doping. Significant intrinsic variation of the shape of the low energy spectrum (and thus changes of the power law) have been observed. These changes occur not only from batch to batch but, surprisingly, may also depend on the impact point of the laser beam onto the surface of the same crystal. [10] As will be shown below, electronic microscopy analyses revealed traces of $BaCuO_2$, BaO_2 and HgO which appear on as grown single crystal surfaces after exposure to air (for a few days). We discovered by a specific study on each of these phases (in bulk form) that their electronic background is able to modify significantly the spectra even for minute quantities.

The third difficulty originates from oxygen doping. All studies carried out on under-doped, optimally doped and over-doped high- T_c superconductors revealed that the low energy electronic spectra is very sensitive to the oxygen doping. [6,11,12]. In contrast with the stoichiometric $Tl - 2201$ compound, optimal doping of the $Hg - 1223$ compound is reached for over-stoichiometry of oxygen. However, excess of oxygen introduces disorder into the Hg -plane. The effect of this disorder (as we will see) is qualitatively to alter the electronic Raman spectrum at low energy, namely introducing a linear-like frequency dependence visible in the B_{1g} channel. In particular, our previous work [13] on electronic Raman spectra on nearly stoichiometric $Hg - 1223$ crystals displayed a frequency dependence of the B_{1g} channel in clear contradiction with the $d_{x^2-y^2}$ symmetry.

As a consequence, in order to avoid the phonon problem, to eliminate traces of parasitic phases and reduce the oxygen disorder coming from δ over-stoichiometry, we have chosen to study strongly under-doped (UD) $Hg - 1223$ crystals (nearly stoichiometric), cleaning the surface just before Raman measurements.

Using these experimental conditions, we report pure electronic Raman spectra in the N and S states of the strongly UD $Hg - 1223$ single crystals. Our main results are summarized as follows: in the S state, the B_{2g} electronic spectrum exhibits a linear frequency dependence at low energy up to 350 cm^{-1} whereas the B_{1g} one shows a cubic frequency dependence up to 700 cm^{-1} [14]. The Raman spectra of the $Hg - 1223$ in the B_{2g} and B_{1g} channels show for the first time a well defined maxima at $5.6\text{ }k_B T_c$ and $9\text{ }k_B T_c$ respectively. Mixed $A_{1g} + B_{2g}$ and $A_{1g} + B_{1g}$ symmetries exhibit a strong maximum close to $6.4\text{ }k_B T_c$.

Below 300 cm^{-1} the electronic spectra of the strongly UD $Hg - 1223$ for all the channels (and up to the gap energy for the B_{1g}) exhibit the electronic scattering expected for a pure $d_{x^2-y^2}$ gap. The quality of the experimental data offers a compelling evidence for the d -wave model. However to reconcile the B_{1g} and B_{2g} peak positions, the B_{2g} Raman

vertices have to be expanded to the next higher order of Fermi surface harmonics [15]. The strong maximum in mixed $A_{1g} + B_{2g}$ and $A_{1g} + B_{1g}$ channels cannot be simply explained by Coulomb screening. These two last points raise new questions about significance (within the $d_{x^2-y^2}$ framework) of the electronic maxima detected on the Raman spectra and the effective Coulomb screening of the A_{1g} channel.

II. CRYSTAL AND SURFACE CHARACTERISATION

The crystallographic structure of $Hg - 1223$ is tetragonal and belongs to the $^1D_{4h}$ space group [16] which allows us a direct comparison with theoretical calculations based on tetragonal symmetries. $HgBa_2Ca_2Cu_3O_{8+\delta}$ single crystals were grown by a single step synthesis as previously described [17,18] resulting in strongly under-doped system with only few stacking defects. Oxygen doping (when needed) was achieved by a separate oxygen annealing yielding slightly underdoped system. They are parallelepipeds with typical $0.7 \times 0.7 \text{ mm}^2$ square cross section and thickness 0.3 mm .

The $[100]$ crystallographic direction lies at 45 degrees of the edge of the square and the $[001]$ direction is normal to the surface. This geometry helps us to align the crystallographic directions with respect to the light polarization [19]. DC magnetization measurements on strongly and slightly UD $Hg - 1223$ crystals under field cooling (FC) and zero field cooling (ZFC) are displayed in Fig.1. A sharp transition occurs at $T_c \sim 121 \text{ K}$, ($\Delta T_c \sim 5 \text{ K}$) for the strongly UD mercurate whereas the slightly UD $Hg - 1223$ exhibits a larger transition width ($\Delta T_c \sim 10 \text{ K}$) with onset of diamagnetism around 133 K and a main transition close to 126 K . This most likely manifests a variation of the oxygen content inside the slightly UD crystals. We estimate the oxygen doping from the $T_c - \delta$ diagram recently established [20]. We find $\delta = 0.12$ for $T_c = 121 \text{ K}$ whereas $T_c = 126 \text{ K}$ corresponds to $\delta = 0.16$ [21]. Up to now, the smallest value of δ experimentally obtained is close to 0.1 . [20,22] Optimal doping is reached for $\delta = 0.19$. Since over stoichiometry (δ) refers to an excess of oxygen atoms randomly arranged within the $Hg-$ planes, optimal doping implies oxygen disorder in the $Hg-$ plane. In order to reduce the oxygen disorder inside the $Hg - 1223$ structure it is therefore more appropriate to study UD $Hg - 1223$ crystals. Moreover the UD $Hg - 1223$ system is closer to a four-fold symmetry than an optimally doped one and is thus more appropriate to symmetry considerations. Resistivity values at T_c is typically $\rho(T_c) \sim (30 - 60) \mu\Omega.cm$ [23] showing the presence of very little (if any) impurities or defects. A particular attention has been paid on the surface quality as already mentioned above. The mirror surface of the freshly as-grown single crystal observed with optical microscope reveal 0.1 mm^2 defect-free domains. However, after a few days of exposure to atmosphere new phases appear due to local decomposition. These new phases undetectable by X-ray diffraction measurements, cluster together ($10 \mu m$) and are identified as $BaCuO_2$, BaO_2 , HgO and $Ca_{0.8}CuO_2$ by a local electron probe analysis. In order to eliminate these phases we have polished the UD $Hg - 1223$ single crystal surface just before Raman measurements. The single crystal is fixed by beeswax and polished by hand using diamonds paste of $0.1 \mu m$ and the adequate polishing felt disc. The crystal is then cleaned with acetone for spectroscopy (containing less than 0.1% of H_2O). We thus regenerate the original high quality defect-free surface of the crystal without local decomposition. Sometimes one or two inclusions of

$Ca_{0.8}CuO_2$ ($40\mu m$) are observed in the bulk and disappear upon further polishing. Scanning tunneling measurements on the polished surface reveals that the polishing streaks are less than $0.01\mu m$ deep. An important optical test is that polished crystal surface under crossed polarization remains dark. This shows that the mechanical polishing does not alter the polarization of the incident light.

III. EXPERIMENTAL DETAILS

Raman measurements were performed with a double monochromator (U-1000 Jobin-Yvon) using a single channel detection (EMI 9863B photomultiplier) and the Ar^+ laser 514.52 nm line. The spectral resolution was set at 2 cm^{-1} . The crystals immediately after polishing were mounted (in the vacuum) on the cold finger of a liquid helium flow cryostat. The temperature was controlled by a CLTS resistance located on the backside of the cold finger. The incident laser spot is less than $100\mu m$ in diameter and the intensity onto the crystal surface was kept below 25 W.cm^{-2} in order to avoid heating of the crystal. The incidence angle was 60 degrees. The polarization is denoted in the usual way: x [100] (a axis), y [010], x' [110], y' [$\bar{1}\bar{1}0$]. In order to compare our experimental data with the theoretical calculations, [1] the pure B_{2g} (xy) and B_{1g} ($x'y'$) symmetries are needed. This requires that the incident electric field have to lie within the xy plane. The incoming light being not normal to the surface, the crystal mount has to be rotated by 45 degrees between the B_{1g} and B_{2g} spectra. The $A_{1g} + B_{1g}$ and $A_{1g} + B_{2g}$ symmetries are obtained from the (xx) and ($x'x'$) polarizations respectively. In order to probe the same area for all symmetries, the impact of the laser beam onto the crystal surface was precisely located before turning the crystal. Only large homogenous surfaces have been selected. The least diffusive spot was selected in order to minimize the amount of spurious elastic scattering. Each Raman spectrum has been obtained after a sum of 40 scans. Each scan has spanned between 25 and 1000 cm^{-1} with an increment of 2 cm^{-1} and an integration time of 3 s.

IV. EXPERIMENTAL RESULTS

In view of the presence of the extra phases, we have performed systematic investigations of the hitherto non reported Raman spectra of the parasitic phases related to mercury compounds, i.e : BaO_2 , $BaCuO_2$, Ba_2CuO_3 , HgO , $HgBaO_2$, $CaCO_3$. Measurements were carried out in the bulk form (powder) in the full range of interest (up to 1000 cm^{-1}) and in the same experimental conditions as the one of the B_{1g} and B_{2g} spectra in the superconducting state (excitation line: 514.52 nm, light under crossed polarization, $T = 13\text{ K}$). The results will be presented separately [24] but can be summarized as follows: All these phases exhibit a nearly flat background together with characteristic phonon peaks [25] except the BaO_2 phase which shows a linear frequency dependent background extending up to 1000 cm^{-1} . This last phase can significantly alter the analysis of Raman spectra as will be shown.

Imaginary part of the Raman response function in the S state and the N state of the strongly UD $Hg - 1223$ compound for the B_{2g} , B_{1g} , $A_{1g} + B_{2g}$ and $A_{1g} + B_{1g}$ channels are displayed in Fig.2. The imaginary part of the susceptibilities in the superconducting and

the normal states are obtained from Raman measurements at $T = 13\text{ K}$ and $T = 295\text{ K}$ respectively. We present in Fig.2 the most representative spectra of a serial of three sets of measurements performed on a strongly UD $Hg - 1223$ crystal. In the following order, we have subtracted the dark current of the photomultiplier [26], the Rayleigh scattering when present, [27] corrected the spectra for the response of the spectrometer and the detector and divided the spectra by the Bose-Einstein factor $n(\omega, T) = [\exp(\hbar\omega/k_B T) - 1]^{-1}$. For the B_{1g} and B_{2g} channels obtained from crossed polarizations the response was scaled up by a factor 1.2 with respect to the A_{1g} mixed channels in order to take into account the absorption of the half wavelength plate inserted between the analyzer and the entrance slit of the spectrometer. The insertion of the half wavelength plate allows us to restore the same polarization inside the spectrometer for all the channels and thus benefit from the best configuration with respect to the grating factor efficiency.

In the S state, we clearly observe a linear frequency dependence at low energy (exponent $n = 1.12 \pm 0.03$ from Fig.2) with a well defined electronic maximum near 450 cm^{-1} for the B_{2g} channel whereas the B_{1g} channel exhibit no measurable electronic scattering below 200 cm^{-1} in the limit of the photomultiplier detection and a non linear frequency dependence (exponent $n = 3.02 \pm 0.1$ from Fig.2) until we reach a maximum around 800 cm^{-1} [14]. We observe in Fig.2, for both B_{1g} and B_{2g} channels, that the intensity of the electronic continuum above 800 cm^{-1} in the N state is two times smaller than for the S state. Temperature dependence of the optical absorption $2\kappa(T)\omega_L/c$ ($\omega_L \approx 19000\text{ cm}^{-1}$) between 13 K and 295 K cannot explain such a large difference since the infra-red reflectance spectra is temperature independent above 1000 cm^{-1} [28] .

In the A_{1g} mixed symmetries, the electronic continuum shows a linear increase with respect to ω with a maximum centered around 550 cm^{-1} . The slope of the electronic scattering is twice larger in the $A_{1g} + B_{2g}$ spectrum than in the $A_{1g} + B_{1g}$ one. This can be attributed to the B_{2g} linear contribution which increases the slope at low energy and broadens the low energy side of the $A_{1g} + B_{2g}$ maximum. As a consequence the $A_{1g} + B_{1g}$ peak is narrower than the $A_{1g} + B_{2g}$ one. A special remark can be made concerning the variation of the intensity of the phonon peaks at 540 and 590 cm^{-1} in the S state in comparison with the N state. The intensities of these two phonon peaks are reduced by a factor of 3 when temperature raises from $T = 13\text{ K}$ to 150 K and decrease again by a factor of 1.2 between 150 K and 295 K . The strong increase of the phonon intensity is clearly a superconductivity related effect since the phonon exhibit two regimes of intensity variations above and below T_c . The Raman phonon activities become similar to those obtained when electric fields are perpendicular to the xy plane i.e. in zz polarization. The intensity enhancement of the phonons in the superconducting state has also been observed in other cuprates and a modified Raman scattering mechanism induced by a redistribution of the excited states in the superconducting state has been proposed. [29]

V. COMPARISON WITH PREVIOUS WORKS

In our previous work on slightly UD $Hg - 1223$ mercurates, contrary to the present work on strongly UD $Hg - 1223$, we reported a linear frequency dependence at low energy

for the B_{1g} spectrum (as well as for the B_{2g}) and one extra shoulder near 800 cm^{-1} for the A_{1g} spectrum beside the 550 cm^{-1} peak. [13] These observations, in contradiction with the $d_{x^2-y^2}$ model, have been interpreted as the signature of an order parameter of lower symmetry. In view of the specific study on the parasitic phases mentioned above, we can now assign the presence of this shoulder to the presence of the $BaCuO_2$ phase. This is also supported by the observation on the A_{1g} spectrum of the intense 640 cm^{-1} phonon peak which is another signature of the $BaCuO_2$ phase. In the same way, we suspect that the multicomponents features observed by Zhou et al. [30] on the Raman spectra of $Hg-1223$ single crystals originate from vibrational modes of HgO and $BaCuO_2$ traces present on the crystal surface. Indeed the 340 cm^{-1} and 640 cm^{-1} peaks are characterisitic of HgO and $BaCuO_2$ spectra and correspond to the oxygen motions of the HgO and $BaCuO_2$ phases. Concerning the linear background previously reported [13] two explanations can be proposed a priori : i) scattering related to parasitic phases on the crystal surface, ii) scattering induced by oxygen doping. Among different phases we quoted above, only the BaO_2 phase which provides frequency linear background and is able to compete even with minute quantities, with the superconducting signal [24]. Quantitative estimate [31] show that less than 1% of BaO_2 is sufficient to produce scattering of the order of magnitude of the electronic Raman coming from the S state. It is therefore mandatory to thoroughly eliminate these phases before any optical investigation. However an additionnal BaO_2 background which extends beyond to 1000 cm^{-1} makes it difficult to interpret the decrease of the continuum above 800 cm^{-1} observed on slightly UD mercurates. Moreover we observed that the temperature dependence of the electronic Raman changed at T_c transition [13]. For these reasons we mainly attribute the linear frequency dependence at low energy in B_{1g} channel to the intrinsic effect of oxygen over-stoichiometry rather than only to the extrinsic BaO_2 phase. Many Raman experiments have been performed on high- T_c superconductors as a function of oxygen doping which reveal changes in the low energy electronic continuum. [6,11,12] Optimally doped (stoichiometric) $Tl-2201$ compounds exhibit a cubic like dependence at low energy whereas the overdoped (over-stoichiometric) $Tl-2201$ compounds show a linear dependence at low energy. [6] Impurity scattering was proposed to explain such a behaviour [32]. In our previous data of slightly UD $Hg-1223$ crystal the linear background extends up to 600 cm^{-1} which means a scattering impurity rate Γ of the order of the gap Δ_0 itself. Such a high scattering rate should strongly reduce the critical temperature. This is in contradiction with $T_c = 126\text{ K}$ and resistivity value ($\rho(T_c) = (30-60)\mu\Omega cm$). We propose that the linear background is the (direct or indirect) effect of localized states generated by oxygen disorder in the Hg -plane. As mentioned in section II, the oxygen disorder is expected to be more important in nearly optimally doped or slightly UD system than the strongly UD one. This is supported by infra-red reflectance measurements [28]. Indeed a strong scattering rate at low energy ($T = 15\text{ K}$) is observed in nearly optimally doped system as well as an intense peak (near 184 cm^{-1}) on the real part of the optical conductivity. This peak is often seen in high- T_c superconductors in presence of oxygen disorder [28,33]. Conversely, in strongly UD system there is no residual scattering at low frequency ($T = 15\text{ K}$) and the 184 cm^{-1} peak is narrower and weaker.

VI. MODEL FOR ELECTRONIC RAMAN SCATTERING

We compare our experimental data with the $d_{x^2-y^2}$ model. In the limit where the superconducting correlation length is much smaller than the optical penetration depth, the imaginary part of the response function for $T \rightarrow 0$ including the screening due to Coulomb interaction is given by : [34]

$$\chi''(\omega) = \text{Re} \left[\chi_{\gamma\gamma}(\omega) - \frac{\chi_{\gamma 1}(\omega)\chi_{1\gamma}(\omega)}{\chi_{11}(\omega)} \right] \quad (1)$$

where $\chi_{\gamma\delta}$ is defined by :

$$\chi_{\gamma\delta}(\omega) = \frac{2\pi N_F}{\omega} \left\langle \frac{\gamma_{\mathbf{k}} \delta_{\mathbf{k}}^* \Delta_{\mathbf{k}}^2}{(\omega^2 - 4\Delta_{\mathbf{k}}^2)^{1/2}} \right\rangle \quad (2)$$

Here $\gamma_{\mathbf{k}}$ and $\delta_{\mathbf{k}}$ are general Raman vertices already described [13]. N_F is the density of states for both spin orientations at the Fermi level, and the brackets indicate an average over the Fermi surface. $\Delta_{\mathbf{k}}$ stands for the superconducting, $\mathbf{k}$ -dependent gap. Eq.(2) vanishes in the limit of large frequency where we should recover the electronic scattering of the normal state. Therefore the normal state scattering contribution is not taken into account in the Raman response function derived in this work.

In the $d_{x^2-y^2}$ model, as computed by Devereaux et al. [1,2], we approximate the Fermi surface as being a cylinder and take: $\Delta_{\mathbf{k}} = \Delta_0 \cos(2\theta)$ for the gap and for the vertices:

$$\gamma_k^{B_{1g}} = \gamma_{B_{1g}} \cos(2\theta), \quad \gamma_k^{B_{2g}} = \gamma_{B_{2g}} \sin(2\theta), \quad \gamma_k^{A_{1g}} = \gamma_0 + \gamma_{A_{1g}} \cos(4\theta) \quad (3)$$

In B_{1g} and B_{2g} symmetries, $\chi_{\gamma 1}$ vanishes which implies that the last term in Eq.(1) drops out. In other words, the B_{1g} and B_{2g} symmetry are not screened. This is not the case for the A_{1g} symmetry, and screening has to be properly taken into account. Nevertheless one sees easily from this equation that any $\mathbf{k}$ -independent contribution to the Raman vertex drops out of the result.

In a pure $d_{x^2-y^2}$ model, the B_{1g} channel is not sensitive to the nodes because the Raman vertex $\gamma_{\mathbf{k}}$ is zero by symmetry for $k_x = \pm k_y$ in contrast, the $k_x = 0$ and $k_y = 0$ regions do contribute, giving weight to the gap Δ_0 in these directions. As a consequence the B_{1g} spectrum displays a weak scattering at low energy and the calculated spectrum shows a ω^3 frequency dependence with a maximum at $2\Delta_0$. Conversely, in the B_{2g} channel, the Raman vertex $\gamma_{\mathbf{k}}$ is zero by symmetry for $k_x = 0$ or $k_y = 0$ or and non zero elsewhere, hence provides weight in the $k_x = \pm k_y$ directions where the nodes are present. The B_{2g} spectrum exhibits a linear low frequency dependence and a smeared gap. Finally the A_{1g} channel is sensitive to both nodes and gap because the Raman vertex $\gamma_{\mathbf{k}}$ doesn't vanish in the $k_x = \pm k_y$, $k_x = 0$ and $k_y = 0$ regions. The A_{1g} channel have to show a linear low ω behaviour. This remains available when we take into account the screening.

To provide a more realistic account of experimental results with respect to the theory we have included life-time effects. We have chosen to include electronic damping by convoluting the bare spectra with a Lorentzian function. Depending on the electronic correlation model, the reduced half width of the lorentzian can be taken as a constant ($\Gamma/2\Delta_0 = a_0$), proportional to ω ($\Gamma/2\Delta_0 = a_1(\omega/2\Delta_0)$) or proportional to ω^2 ($\Gamma/2\Delta_0 = a_2(\omega/2\Delta_0)^2$).

The B_{1g} experimental spectrum exhibits a nearly cubic frequency dependence up to 700 cm^{-1} . Such a behaviour imposes, whatever the type of damping, to use small values for the a_0, a_1, a_2 parameters. For $a_0 = a_1 = a_2 = 0.06$ we obtain satisfactory fits for the B_{1g} spectrum, conversely if we increase by a factor 2 the reduced parameters, fits are in disagreement with experiments. As already explained [13] we have chosen to display fits for $\Gamma(\omega) = a_1\omega$. The calculated curves of the B_{1g} and B_{2g} spectra for three values of the a_1 parameter are shown in Fig. 3. The half width at half maximum of the B_{1g} peak is seen to double as the a_1 parameter is increased by a factor 5. This dependence reduces the choice of the a_1 parameter to values close to 0.06 in order to be in agreement with the experimental data. This value of the damping parameter a_1 should be compared with the value of 0.15 previously obtained on more oxygen disordered $Hg - 1223$ [13]. The fact that in this latter case T_c is increased may appear paradoxical. We are forced to conclude, in that case, that the effect of doping overwhelms the effect of scattering by disorder. A similar conclusion can be reached from infrared-measurements [28].

The theoretical spectra in B_{1g} , B_{2g} and A_{1g} screened channels for $a_1 = 0.06$ are displayed in Fig. 4. Fits have been calculated from the strongly UD $Hg - 1223$ data. The $2\Delta_0$ gap has been defined from the B_{1g} spectrum since the B_{1g} vertex probes directly the Δ_0 amplitude. We have chosen to adjust the lower part of the calculated curves to the experimental data. Below 300 cm^{-1} we find a very good agreement between theoretical and experimental data for all the three channels and up to the gap for the B_{1g} channel. However the fits are not satisfactory at higher energy (above 300 cm^{-1}) for the B_{2g} and A_{1g} channels. Firstly the B_{2g} maximum of the calculated spectrum (700 cm^{-1}) is clearly far away from the B_{2g} experimental one (450 cm^{-1}) as it is seen in Fig. 4. As a consequence the calculated frequency ratio between the B_{1g} and B_{2g} peaks positions (1.2) do not correspond to the experimental one (1.6) obtained from the $Hg - 1223$ spectra. Secondly the calculated curve of the A_{1g} screened spectrum is a broad peak centered around 700 cm^{-1} whereas we get experimentally a sharper (width at half maximum : 200 cm^{-1}) and more intense peak near 550 cm^{-1} .

Concerning the first point (B_{2g} spectrum) we propose to expand the B_{2g} vertex to higher order as was already done for the A_{1g} vertex. The justification of this procedure is based on the fact that the Fermi surface is anisotropic. The B_{2g} vertex is expected to be more sensitive to additional harmonic terms than the B_{1g} vertex because the B_{2g} vertex probes a region where the gap changes drastically (nodes of the gap). It is then possible to reconcile experiments to the $d_{x^2-y^2}$ model by expanding the B_{2g} vertex to the next order of the Fermi surface harmonics. [1] Indeed including higher order Fermi surface harmonics in the Raman vertices change the relative positions of the B_{1g} and B_{2g} peaks. Cardona et al. [35] showed that the B_{1g} peak shifts down when varying the α parameter related to the contribution of the second Fermi surface harmonics : $\gamma_{B_{1g}}(\cos(2\theta) - \alpha\cos(6\theta))$. By taking $\gamma_k^{B_{2g}} = \gamma_{B_{2g}}(\sin(2\theta) - \beta\sin(6\theta))$, we find that the B_{2g} peak softens as β increases (see Fig. 5). As expected this softening is even larger when we consider the B_{2g} vertex than for the B_{1g} vertex. The calculated curve of the B_{2g} spectrum obtained for $\beta = 0.4$ is displayed on Fig. 4. We find an agreement between our calculated and experimental curves up to 700 cm^{-1} . These results are consistent with the $d_{x^2-y^2}$ model under considering the deviation away from the cylindricity of the Fermi surface when calculating the vertices. The deviation of the Raman vertex is assumed larger than the one of the wave-vector on the Fermi surface.

$(\delta\gamma)_F \gg (\delta k)_F$. Best fits could be further improved by taking the electronic scattering of the normal state but this is not done here.

Concerning the second point (A_{1g} spectrum) the Coulomb screening present in the Raman scattering process might be not as efficient as it has been considered. Strong mass fluctuations induced by inter-layer coupling or several sheets of CuO_2 planes as proposed elsewhere, [35] could decrease the A_{1g} scattering efficiency. On the other hand expansion to higher order of the A_{1g} vertex have to be explored.

VII. CONCLUSION

In conclusion we have specially investigated strongly under-doped $HgBa_2Ca_2Cu_3O_{8+\delta}$ single crystals in order to reduce the oxygen disorder in the $Hg - plane$ taking care to eliminate parasitic phases on the crystal surface. In these improved experimental conditions we are able to report with good accuracy the pure electronic Raman scattering (without subtraction of phonons) in the B_{2g} , B_{1g} , $A_{1g} + B_{2g}$ and $A_{1g} + B_{1g}$ channels. The $d_{x^2-y^2}$ model fits quite well with the low energy part (below 350 cm^{-1}) of the spectra for the B_{2g} and A_{1g} symmetries and up to the gap energy for the B_{1g} one. However, in order to reconcile with the $d_{x^2-y^2}$ model, the upper part of the B_{1g} and B_{2g} spectra (above 350 cm^{-1}), we have to expand the B_{2g} vertex to the next order of Fermi surface harmonics. The sharp and intense electronic maximum in mixed A_{1g} symmetries is not easy to interpret in the framework of the $d_{x^2-y^2}$ model. This last point raises new questions on the A_{1g} screening efficiency. Experimentally, this work on near stoichiometric $Hg - 1223$ compounds as compared to previous work on less stoichiometric compounds highlights the importance of oxygen disorder on the low energy excitations as revealed by the frequency dependence, cubic or linear of the electronic Raman spectra. This surprisingly strong effect already reported in a number of high- T_c cuprates is understood in only a qualitative way and bears directly on the dynamic of the low lying electronic states in the superconducting state.

VIII. ACKNOWLEDGEMENTS

We thank T. Timusk, J. J. McGuire, R. Combescot, N. Bontemps, N. Sandler, B. Jusserand, M. T. Béal-Monod and R. Lobo for very fruitful discussions. We are grateful to M. Jouanne and J. F. Morhange for allowing us to use Raman spectrometer (LMDH, Paris VI). We also wish to acknowledge S. Poissonnet and L. Schmirgeld-Mignot for the chemical analysis by electron probe.

REFERENCES

- [1] T. P. Devereaux, D. Einzel, B. Stadlober, R. Hackl, D. H. Leach and J. J. Neumeier, Phys. Rev. Lett. **72**, 396, (1994); T. P. Devereaux and D. Einzel, Phys. Rev. B **51**, 16336 (1995). T. P. Devereaux and D. Einzel, Phys. Rev. B **54**, 15547, (1996).
- [2] X. K. Chen, J. C. Irwin, H. J. Trodhal, T. Kimura and K. Kishio, Phys. Rev. Lett. **73**, 3290 (1994).
- [3] N. Nemetschek, R. Hackl, M. Opel, R. Philipp, M. T. Béal-Monod, J. B. Bieri, K. Maki, A. Erb and E. Walker, Eur. Phys. J. B **5**, (1998).
- [4] T. Staufer, R. Nemetschek, R. Hackl, P. Müller and H. Veith, Phys. Rev. Lett. **68**, 1069 (1992).
- [5] L. V. Gasparov, P. Lemmens, M. Brinkmann, N. N. Kolesnikov and G. Güntherodt, Phys. Rev. B **55**, 1223 (1997).
- [6] Moonsoo Kang, G. Blumberg, M. V. Klein and N. N. Kolesnikov, Phys. Rev. Lett. **77**, 4434, (1996).
- [7] A. Sacuto, A. Lebon, D. Colson, A. Bertinotti, J.-F. Marucco and V. Viallet, Physica C **259**, 209 (1996). Similar observations have been made by X. Zhou et al. Phys. Rev. B **55**, 12770 (1997).
- [8] A. Sacuto, R. Combescot, N. Bontemps, P. Monod, V. Viallet and D. Colson, Europhys. Lett. **39**, 207 (1997).
- [9] E. Ya. Sherman, R. Li and R. Feile, Phys. Rev. B **52**, R 15757, (1995).
- [10] This last observation was made by inserting a video camera just behind the entrance slit of the spectrometer which allowed us to precisely choose ($50\text{ }\mu\text{m}$) the laser spot on the crystal surface.
- [11] L. V. Gasparov, P. Lemmens, N. N. Kolesnikov and G. Güntherodt, Phys. Rev. B **58**, 11753 (1998).
- [12] X. K. Chen, J. G. Naeini, K. C. Hewitt and J. C. Irwin, R. Liang and W. N. Hardy, Phys. Rev. B **56**, R513, (1997).
- [13] A. Sacuto, R. Combescot, N. Bontemps, C. A. Müller, V. Viallet and D. Colson, Phys. Rev. B **58**, 11721, (1998).
- [14] Preliminary results on strongly UD $Hg - 1201$ mercurates ($T_c \sim 55\text{ K}$) exhibit the same behaviour as the strongly UD $Hg - 1223$ one at low energy i.e: linear and cubic dependence for B_{2g} and B_{1g} respectively.
- [15] P. B. Allen, Phys. Rev. B **13**, 1416, (1976).
- [16] M. Cantoni, A. Schilling, H.-U. Nisen and H. R. Ott, Physica C **215**, 11 (1993).
- [17] D. Colson, A. Bertinotti, J. Hammann, J.-F. Marucco, A. Pinatel, Physica C **233**, 231 (1994); A. Bertinotti et al. Physica C **250**, 213 (1995).
- [18] A. Bertinotti, D. Colson, J.-F. Marucco, V. Viallet, J. Le Bras, L. Fruchter, C. Marcenat, A. Carrington, J. Hammann, in "Studies of High Temperature Superconductors" edited by Narlikar, Nova Science Publisher (NY) (1997).
- [19] The uncertainty inherent to this procedure is believed to be negligible.
- [20] V. Viallet-Guillem, PhD thesis, Univresty of Paris Sud, (1998).
- [21] In reference [13] we quoted δ less than 0.1 for $T_c = 126\text{ K}$. This value was later corrected by thermogravimetry measurements to $\delta = 0.16$. Hence the crystal used in this previous work belongs to slightly UD system.

- [22] A. Fukuoka, A. Tokiwa-Yamamoto, M. Itoh, R. Usami, S. Adachi and K. Tanabe, Phys. Rev. B **55**, 6612 (1997).
- [23] A. Carrington, D. Colson, Y. Dumont, C. Ayache, A. Bertinotti and J. F. Marucco, Physica C **234**, 1 (1994).
- [24] A. Sacuto, D. Colson, J. Cayssol, B. Jusserand and P. Monod in M2S-HTSC-VI proceedings, will be published in Physica C.
- [25] the HgO phase exhibits two phonon peaks at 340 cm^{-1} and 560 cm^{-1} . The $HgBaO_2$ spectrum shows three peaks at 200 cm^{-1} , 340 cm^{-1} and 645 cm^{-1} . The BaO_2 spectrum shows a phonon structure close to 840 cm^{-1} . The $BaCuO_2$ spectrum exhibits two peaks at 590 cm^{-1} and 640 cm^{-1} and one shoulder near 800 cm^{-1} . The Ba_2CuO_3 spectrum presents an intense phonon peak at 560 cm^{-1} and the $CaCO_3$ spectrum exhibits three peaks at 160 cm^{-1} , 289 cm^{-1} and 712 cm^{-1} .
- [26] The dark current is constant and its intensity corresponds approximatively to 30% of the B_{2g} signal at 13 K and above 800 cm^{-1} .
- [27] There is no correction for cross polarization (B_{1g} and B_{2g}) and small contribution is removed by extrapolation below 50 cm^{-1} for parallel polarizations (A_{1g}).
- [28] J. J. McGuire et al. preprint.
- [29] O. V. Misochko, E. Ya. Sherman, N. Umesaki, K. Sakai, S. Nakashima, Phys. Rev. B **59**, 11495, (1999).
- [30] X. Zhou, M. Cardona, D. Colson and V. Viallet Physica C **282-287**, 1007, (1997).
- [31] We have estimated the Raman intensity as a function of the BaO_2 phase percent. It was done from the Raman spectrum of the BaO_2 powder (in the bulk form) obtained in the same experimental conditions as the B_{2g} and B_{1g} spectra in the S state. 100% of illuminated bulk of BaO_2 gives 500 arb. units at 300 cm^{-1} .
- [32] T.P. Devereaux, Phys. Rev. Lett. **74**, 4313, (1995).
- [33] D. N. Bazov, B. Dabrowski and T. Timusk, Phys. Rev. Lett. **81**, 2132, (1998).
- [34] M. V. Klein and S. B. Dierker, Phys. Rev. B **29**, 4976 (1984).
- [35] M. Cardona, T. Strohm and X. Zhou, Physica C **282-287**, 222, (1997); T. Strohm and M. Cardona, Phys. Rev. B **55**, 12725, (1997).

Figure Captions

FIG. 1 DC magnetization in FC and ZFC of strongly and slightly UD Hg-1223 single crystals. The curve of the slightly UD Hg-1223 is taken from the reference [13].

FIG. 2 Imaginary part of the electronic response function of the strongly UD Hg-1223 single crystal in the B_{2g} , B_{1g} , $A_{1g} + B_{2g}$ and $A_{1g} + B_{1g}$ channels. Solid and dashed lines correspond respectively to the superconducting and the normal state obtained from $T = 13\text{ K}$ and $T = 295\text{ K}$. No phonon subtraction was necessary.

FIG. 3 Theoretical curves of the B_{1g} and B_{2g} spectra for different values of the a_1 damping parameter ($\Gamma = a_1\omega$).

FIG. 4 Comparison between the experimental data and the $d_{x^2-y^2}$ model. The calculated curves obtained from the B_{1g} , B_{2g} and A_{1g} vertices defined in Eq. (3) are shown in solid lines. The dashed line corresponds to the B_{2g} calculated curve including the second order expansion of the B_{2g} vertex ($\beta = 0.4$). For all the calculations $a_1 = 0.06$.

FIG. 5 Theoretical curves of the B_{2g} response for $\beta = 0, 0.4, 0.8$; ($a_1 = 0.06$).









